

Stucco Italiano



STUCCO CEMENTITIOUS SELFLEVELLING

DESCRIPTION

STUCCO CEMENTITIOUS SELFLEVELLING creates a luxurious, natural, smooth finish with a mottled look, suitable for interior and exterior floor applications. Applied with a steel trowel onto primed concrete and other surfaces (even directly onto tiled surfaces) it creates an appealing look

PURPOSE

STUCCO CEMENTITIOUS SELFLEVELLING provides a tough, waterproofing durable selfleveling cement based plaster for interior and exterior floor finishes, available in a range of colours.

ADVANTAGES

- STUCCO CEMENTITIOUS SELFLEVELLING is user-friendly;
- It is easy to apply;
- There is no need to go back to finish off the floor or smooth down trowel marks;
- It is time saving;
- It is selfleveling;
- It has a smooth finish;
- It creates a seamless floor;
- It is ideal for outdoor use.

APPLICATION

Necessities

1 bag of 20kg STUCCO CEMENTITIOUS SELFLEVELLING;
3.0lt of Water; 40lt mixing bowl; gloves; steel trowel; masking tape; drop sheets; paint brushes and rollers.

Preparation

The concrete floor surface must be sound clean and free from any dust, saline deposits, greasiness or any materials that can prevent binding. Saline deposits and greasiness can be washed off with washing soda.

The floors must be inspected for any cracks or weakness in which case it has to be repaired using the STUCCO FLOOR FIXING KIT and or a thin layer of the same CEMENTITIOUS SELFLEVELING before applying the final STUCCO CEMENTITIOUS SELFLEVELLING.

The ideal surface for application of STUCCO CEMENTITIOUS SELFLEVELLING is a wood floated floor screed.

One does not need to apply any bonding agent before applying the Stucco CSL.

Apply masking tape around edges and joints.

Prime the floor with POWERSCREED LIQUID and let it dry.

Make sure the floor is thoroughly sealed off.

Mixing Instructions

Decant the 3.0lt water into the 40lt mixing bowl.

Gradually add the STUCCO CEMENTITIOUS SELFLEVELLING powder, while continuously mechanically mixing the mixture to prevent lumps from forming, until the full amount of 20kg STUCCO CEMENTITIOUS SELFLEVELLING is thoroughly mixed..

Stucco Italiano



Product can be poured through a sieve to remove any lumps.

A pan mixer is ideal for mixing and preventing lumps.

Application

After mixing, pour the contents of the mixing bowl onto the floor in longitudinal beads and spread it with a steel trowel to a thickness of 2 – 3 mm.

Continue mixing the product during application to prevent the product from settling.

Spread the contents around and smooth it down in irregular movements to create a mottled finish.

Work from one corner/edge/joint, always keeping a wet edge to prevent unsightly dry joints.

Do not lift the trowel so that the product is dripping.

Leave to cure for at least 48 hours.

SEALERS

The day after finishing the floor, apply one coat of STUCCO COLOUR FASTENER and let dry over night. Apply two coats of STUCCO FLOOR SEALER GLOSS, LOW SHEEN, MATT 18 hours apart or STUCCO EPOXY FLOOR SEALER with 24 hour intervals between first and second coat.

Allow the last coat of sealer to cure for at least 48 hours before walking on the floor.

TECHNICAL DATA

Type:	Cement based
Drying time:	48 hours @ 20°C
Shelf life:	6 months
Coverage:	5m ² per kit (one coat)
Packaging:	20kg powder in paper bags 2.8lt water in plastic bottles
Storage:	Store in a cool dry place
Compressive Strength:	35MPa

WARNING

Do not ingest. Keep away from children and pets. Do not empty into drains.

PRECAUTIONS

Wear rubber gloves. In the event of contact with eyes or skin, rinse thoroughly with cold water. If irritation or discomfort occurs, seek medical advice.

Stucco Italiano



MANUFACTURED BY

Stucco Italiano
25 Industria Rd
Brackenfell
Tel: 021- 982 0006
Fax: 021-982 3796
E-mail: info@stuccoitaliano.co.za
www.stuccoitaliano.co.za